



TECHNICAL DATA SHEET No 128

BODY 634 4:1 HS FILLING PRIMER

GENERAL TECHNICAL DESCRIPTION

2K acrylic system sanding primer
 Direct application over brand new and used OEM plastic bumpers without the use of an intermediate adhesion promoter
 Excellent filling properties
 Excellent mechanical properties even on plastic bumpers
 Easy to sand

SURFACE

On old, sanded paint work
 Unsanded cataphoresis OEM panels (E-COAT)
 Fiberglass
 Clean and sanded steel panels
 HB BODY Polyester Fillers
 HB BODY Wash Primer
 P961 Etch Primer
 Over new and used plastic bumpers, properly degreased

PRETREATMENT/CLEANING OF SUBSTRATE



Clean substrate using a soft cloth and 770 ANTISIL NORMAL / 771 ANTISIL FAST DEGREASER.

Make sure the surface is first wiped dry and then air dried.

PRODUCT APPLICATION: As sanding primer

Mix 4 parts PRIMER with 1 part BODY 625 HARDENER FOR PRIMERS Pot life: 55 - 70 min / 23°C (73°F)	Addition 15 - 20% 740 ACRYL NORMAL or 741 ACRYL SLOW THINNER / REDUCER	Ready to spray: 26 - 34 s DIN 4 / 20°C (68°F)	Compliant spray gun 1.5 - 1.8 mm 2 - 2.5 bar (29 - 36 psi) 2x coats = 120 - 150 µm (4.7 - 5.9 mil)
1.5 - 1.7 mm 1.5 - 2 bar (22 - 29 psi) 2x coats = 120 - 150 µm (4.7 - 5.9 mil)	5 - 10 min / 23°C (73°F) Flash off time	1 - 2 h / 23°C (73°F) 20 - 30 min / 60°C (140°F) panel temperature	Short wave 5 - 8 min distance 60 - 70 cm
P 400 - P 500	P 600 - P 1000 Sanding by hand, wet	It can be painted over with all HB BODY Mix Systems	

PRODUCT APPLICATION: For plastic parts (PE - PP - ABS - TSOP etc)

Direct application without the need of an adhesion promoter

Dry sanding P 180 - P 220 (never with a scotch brite)	Clean substrate using a soft cloth and 770 ANTISIL NORMAL / 771 ANTISIL FAST DEGREASER Make sure the surface is first wiped dry and then air dried	Mix 4 parts PRIMER with 1 part BODY 625 HARDENER FOR PRIMERS Pot life: 55 - 70 min / 23°C (73°F)	Addition 50 - 60% 740 ACRYL NORMAL or 741 ACRYL SLOW THINNER / REDUCER
Ready to spray: 16 - 18 s DIN 4 / 20°C (68°F)	Compliant spray gun 1.3 - 1.4 mm 2 - 2.5 bar (29 - 36 psi) 2 - 3x coats = 60 - 80 µm (2.3 - 3.1 mil)	1.3 - 1.4 mm 1.5 - 2 bar (22 - 29 psi) 2 - 3x coats = 60 - 80 µm (2.3 - 3.1 mil)	5 - 10 min / 23°C (73°F) Flash off time
1 - 2 h / 23°C (73°F)	P 400 - P 500	P 600 - P 1000 Sanding by hand, wet	It can be painted over with all HB BODY Mix Systems

PRODUCT APPLICATION: As "wet on wet" primer


Mix 4 parts PRIMER with 1 part H 729 HARDENER FOR PRIMERS NORMAL
Pot life: 45 min / 23°C (73°F)



Addition 50 - 60% 740 ACRYL NORMAL or 741 ACRYL SLOW THINNER / REDUCER



Ready to spray: 16 - 18 s
DIN 4 / 20°C (68°F)



Compliant spray gun
1.3 - 1.4 mm
2 - 2.5 bar (29 - 36 psi)
1 - 2x coats = 20 - 30 µm (0.8 - 1.2 mil)



1.3 - 1.4 mm
1.5 - 2 bar (22 - 29 psi)
1 - 2x coats = 20 - 30 µm (0.8 - 1.2 mil)



20 - 30 min / 23°C (73°F)
Flash off time



It can be painted over with all HB BODY Mix Systems

Notes:

- On a "wet on wet" application H 729 HARDENER FOR PRIMERS must be used (never BODY 625 HARDENER)
- Never apply "wet on wet" over polyester fillers. High risk of mapping appearance after clear coating

FLASH POINT

27°C / 80°F

SPECIFIC GRAVITY

1.5 g/cm³

SOLID CONTENT

(NO THINNER)

74% Weight

VOC (2004/42/EC)

This is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 540 g/L. The VOC content in the ready for use form of this product is 540 g/L.
2004/42/IIIB(c)(540)540

THEORETICAL COVERAGE

6 m² / l at 120 micron (4.7 mil) dry film thickness

CLEANING OF EQUIPMENT

Clean after final use with 740 ACRYL NORMAL thinner / reducer

REMARKS

- Allow for additional time for combi spray booths to reach the desired temperature
- Application only with the recommended hardeners and thinners / reducers
- Do not use at temperatures below 15°C (59°F)
- Do not apply the primer as 'wet on wet' on TPA surfaces

Caution:

Always check with a cloth and thinner if the panel is an OEM (E-COAT) panel. On OEM (E-COAT) panels, the cloth stays clean. Then clean the surface with 770 ANTISIL and the "wet on wet" procedure is followed without sanding prior to BODY 634 application.

STORAGE SHELF LIFE

- Store in a cool place (+5°C - +25°C) (41°F - 77°F) and use within 12 months for best results. Guaranteed shelf life of 24 months in unused original containers



Always wear protective equipment



Follow the application instructions mentioned in this TDS

2K paint systems tend to react with water, hence all the equipment used must be moisture free. Isocyanates may cause skin sensitization. More specifically, care should be taken when handling the material. Anyone with a history of histaminic conditions, or respiratory problems should consult the doctor first.

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

SEPTEMBER 2021